

Plytanium® plywood exterior siding is an exterior-grade panel that is ideal for siding applications from new home construction and remodeling to do-it-yourself projects.

Available Types & Sizes (Sized for 4' x 8')

Length (Minimum)	7'-11 ⁷ / ₈ " (2.435 m)
Width (Minimum)	3'-11 ⁷ / ₈ " (1.216 m)
Siding Types	T1-11 Reverse Board & Batten (RB & B) No Groove
Finish	Rough sawn or scratch sand
Groove Spacing	T1-11 – 4" on-center or 8" on-center RB & B – 12" on-center

Building Code Performance Categories, Panel Thickness

- 11/32 CAT, 0.328" (8.33 mm)
- 19/32 CAT, 0.578" (14.68 mm)

Specifications

Length/Width Tolerance	+0, -1 ¹ / ₁₆ " (+0, -1.6 mm), based on 4' or 8' value
Straightness Tolerance	±1 ¹ / ₁₆ " (±1.6 mm)
Squareness Tolerance	±1 ¹ / ₈ " (±3.2 mm)
Primary Species	Southern Yellow Pine
Testing Agency	APA®-The Engineered Wood Association
Classification	Exterior – Plywood suitable for repeated wetting and redrying or long-term exposure to weather and other conditions of similar severity.
Code Fire Classification	Class III or C
Flame Spread Rating	75-200, smoke-developed index <450
Building Code Compliance	PS 1-09

Other Information

Forestry Certification Plytanium siding panels are made from Sustainable Forestry Initiative® (SFI®) certified responsible wood sources.



Formaldehyde Emission Plytanium siding panels contain no added urea formaldehyde resins. Emission levels for certified PS 1 structural panels are exempt by the California Air Resources Board (CARB) in the Composite Wood Air Toxic Control Measure (ATCM) and phenolic bonded structural panels are exempt from testing or monitoring by HUD in the Manufactured Home Construction and Safety Standards.

Manufacturing Locations

Location	APA Mill Number	Zip Code	Harvest Radius
Camden, TX	515	75934	90 miles
Corrigan, TX	516	75939	90 miles
Dudley, NC	348	28333	80 miles
Emporia, VA	230	23847	40 miles
Gurdon, AR	517	71743	60 miles
Madison, GA	404	30650	100 miles
Prosperity, SC	329	29127	80 miles
Taylorsville, MS	282	39168	50 miles